

Super-Tek Dual Mix  
HIGH PERFORMANCE THIN-SET MORTAR

For installing ceramic, quarry, marble, pavers and other natural stone tiles on floors and walls.

1. MANUFACTURER

Super-Tek Products, Inc.  
25-44 Borough Place  
Woodside, NY 11377 USA  
Telephone: (718) 278-7900  
Fax: (718) 204-6013  
Fax back on Demand: (718) 278-5311  
Internet: [www.super-tek.com](http://www.super-tek.com)

2. PRODUCT DESCRIPTION

High Performance Portland cement thin-set mortar for interior installation of ceramic, quarry, marble, pavers and other natural stone tiles on floors and walls.

- o Easy to Trowel
- o Excellent Bond
- o Exceeds ANSI A118.1
- o Residential/Commercial Use

3. INSTALLATION

APPROVED SUBSTRATES: Properly prepared concrete, concrete block, plumb and true masonry, gypsum board, and cured Portland cement beds.

DO NOT USE OVER: Hardwood, plywood, existing tile, cement backer board, masonite, chipboard, flakeboard, presswood, asbestos board, vinyl flooring, lauan plywood, OSB, metal, gypsum based levelers, glass, plastic or other similarly unstable substrates.

PLEASE NOTE: 1) Latex additive must be used when installing porcelain tiles, for installations over cement backer board or exterior grade plywood, and for exterior applications. 2) Not for use with Green Marble or similar moisture sensitive tiles prone to "curling". 3) Use white thin-set mortar when installing light colored marble and light colored grouts.

INSTALLATION: All installations must be set in accordance with the most recent publication of the Tile Council of America's "Handbook For Ceramic Tile Installations" and the following guidelines.

MIXING: Add approximately 6 quarts of cool, clean water to 50 lbs. of Dual Mix Thin-set and mix to a thick, paste-like consistency. Use slow speed bucket mixers or mortar box for mixing, do not use high-speed drills. Allow mixture to slake (stand) for 10-15 minutes, and then remix before applying. Mixture should be stirred occasionally during use, do not retemper. Pot life is approximately 2-3 hours depending on temperature and humidity.

APPLICATION: All surfaces must be clean and free of dust, grease, wax, and foreign matter. Using pressure, apply a thin skim coat with flat edge of trowel. Then using the proper sized notched trowel apply a second coat to form ridges. Trowel only in an area that can be tiled before the mortar skins over (15-20 minutes). If mortar skins over, remove and apply fresh mortar. Apply dry tiles with pressure and a slight twisting motion. Immediately beat tiles in to ensure maximum contact and bond. After setting several tiles, remove one or two and inspect, making sure tile backs are 100% covered with mortar. Back buttering of

tiles may be necessary to insure 100% coverage. Do not use at temperatures below 45°F (7°C) or above 95°F (35°C).

**CURING:** Dual-Mix may be damp cured with water for three days to increase hardness prior to grouting. All traffic should be kept off of floors for a minimum of 48 hours. Jobsite temperature must remain between 45°F and 95°F for a minimum of 72 hours after installation.

**GROUTING:** : May be accomplished in 24 hours if tiles are firmly set and kneeling boards are used. To ensure quality joints use one of Super-Tek's high performance grouts.

**WARNING! EYE AND SKIN IRRITANT. BREATHING DUST MAY CREATE LUNG CANCER RISK. CONTAINS CRYSTALLINE SILICA AND PORTLAND CEMENT.** Avoid contact with eyes, skin and clothing. Avoid breathing dust. Wash thoroughly after handling. In case of eye contact, immediately flush with plenty of water for at least 15 minutes, consult a physician immediately. For skin contact, wash affected area with soap and water. For additional information, see Material Safety Data Sheet (MSDS) for this product.

#### 4. TECHNICAL DATA

Dual Mix mixed with water

ANSI A118.1 -1999 Test/Test Results

28 Day Shear Strength (Glazed Wall Tile) ----- >410 psi

28 Day Shear Strength (Impervious Ceramic Mosaic Tile) ----- >298 psi

TCA Service Rating ASTM C-627 ----- > Extra Heavy

#### Physical Properties

Open Time at 72°F (22°C) ----- >50 minutes

Pot Life at 72°F (22°C) ----- 2-3 hours

#### 5. COVERAGE:

Ceramic, quarry, vitreous & natural stone tiles (includes lug-backed tiles) up to 12" X 12" in size: 1/4" x 3/8" x 1/4" Square-notched trowel. Approx. coverage 50-55 sq. ft. per 50 lb. bag.

Ceramic, quarry, & vitreous tiles up to 6" X 6" in size: 1/4" x 1/4" x 1/4" Square-notched trowel. Approx. coverage 75-85 sq. ft. per 50 lb. bag.

Ceramic mosaics: 3/16" x 3/16" V-notched (saw tooth) trowel. Approx. coverage 100-115 sq. ft. per 50 lb. bag.

**Trowel Sizes Note:** When installing tiles larger than 12" x 12" use appropriate sized trowel to ensure 100% coverage of tile back (i.e. 3/4" U- notched trowel). Coverage will vary.

#### 6. PACKAGING:

25 lb & 50 lb bags. Color: Grey & White.

#### 7. SHELF LIFE:

One year when stored in original packaging in a dry, ventilated place. Exposure to moisture will shorten the shelf life.

#### 8. NOTICE AND WARRANTY DISCLAIMER:

The MANUFACTURER has provided the enclosed Instructions/Recommendations [I/R] to assist the USER in the application of this product. These I/Rs are not warranted to be comprehensive, complete, thorough or conclusive as regards any specific installation. It is the USER'S obligation to ensure that the product is suitable for it's intended use and that it is compatible with existing conditions or applications of other coinci-

dent or adjoining materials. The liability of the SELLER and the MANUFACTURER, whether express or implied, whether in contract or in tort, arising out of warranties, representations, instructions or defects from any cause shall be limited exclusively to replacing the product, provided the same is proved defective, or refunding the purchase price upon return of the unused product. In no event will SELLER or MANUFACTURER be liable for consequential damages, including but not limited to, loss of materials, costs of labor, loss of profits, costs of replacement goods, or other commercial loss. The USER accepts the product AS IS, and without warranties expressed or implied.

#### 9. TECHNICAL ASSISTANCE

Information is available by calling Super-Tek Products:

Mon. thru Fri. (Hours 8:00 AM to 4:30 PM EST)

Telephone: (718) 278-7900 ext. 111

FAX: (718) 204-6013

To receive product information or Material Safety Data Sheets via fax 24 hours 7 days, call: (718)278-5311.